# Fluid Compatibility Table

| Item \ Material | NBR | EPDM | FKM | CR | ACM | FVMQ | VMQ |
|---|---|---|---|---|---|---|---|
| ASTM OIL NO. 1 | ◎ | △ | ◎ | ◎ | ◎ | ◎ | ◎ |
| NO. 3 | ◎ | △ | ◎ | △ | ◎ | ◎ | ⊙ |
| ASTM REFERENCE FUEL A | ◎ | △ | ◎ | ○ | ○ | ◎ | △ |
| B | ◎ | △ | ◎ | △ | △ | ◎ | △ |
| C | ○ | △ | ◎ | △ | △ | ○ | △ |
| D | ○ | △ | ◎ | △ | △ | × | △ |
| MILK | ◎ | ◎ | ◎ | ◎ | △ | ◎ | ◎ |
| ACETALDEHYDE | ⊙ | ○ | △ | ⊙ | △ | △ | ○ |
| ACETAMIDE | ◎ | ◎ | ⊙ | ◎ | △ | ◎ | ○ |
| ACETIC ACID, GLACIAL | ○ | ○ | △ | △ | △ | △ | ○ |
| HOT, HIGH PRESS | △ | ⊙ | △ | △ | △ | △ | ⊙ |
| 5% | ○ | ◎ | ◎ | ◎ | △ | ○ | ◎ |
| ACETONE | △ | ◎ | △ | △ | △ | △ | △ |
| ACETOPHENONE | △ | ◎ | △ | △ | △ | △ | △ |
| ACETYLENE | ◎ | ◎ | ◎ | ○ | × | × | ○ |
| AMMONIA, GAS, COLD | ◎ | ◎ | △ | ◎ | △ | △ | ◎ |
| GAS, HOT | △ | ○ | △ | ○ | △ | △ | ◎ |
| LIQUID (ANHYDROUS) | ○ | ◎ | △ | ◎ | △ | △ | ○ |
| AMMONIUM HYDROXIDE, 3 MOLAR | ◎ | ◎ | ○ | ◎ | △ | ◎ | ◎ |
| CONCENTRATED | △ | ◎ | ⊙ | ◎ | △ | ◎ | ◎ |
| AMYL ACETATE | △ | ◎ | △ | △ | △ | △ | △ |
| ANDEROL ,L-774 (DI-ESTER) | ○ | △ | ◎ | △ | ○ | ○ | △ |
| ANTIFREEZE | ◎ | ◎ | ◎ | ◎ | △ | × | ◎ |
| ANILINE | △ | ○ | ⊙ | △ | △ | ⊙ | △ |
| ANSUL ETHER 161 OR 181 | ⊙ | ⊙ | △ | △ | △ | ⊙ | △ |
| AROCLOR, 1248 | ⊙ | ○ | ◎ | △ | △ | ○ | ○ |
| 1254 | △ | ○ | ◎ | △ | △ | ○ | ⊙ |
| 1260 | ◎ | × | ◎ | ◎ | △ | ◎ | ◎ |
| ASKAREL | ○ | △ | ◎ | △ | △ | ○ | △ |
| AUTO. TRANCMISSION FLUID | ◎ | △ | ◎ | ○ | ◎ | × | △ |
| BEER | ◎ | ◎ | ◎ | ◎ | △ | ◎ | ◎ |
| BENZALDEHYDE | △ | ◎ | △ | △ | △ | △ | △ |
| BENZENE | △ | △ | ◎ | △ | △ | ◎ | △ |

**COMPATIBILITY RATING**

◎:SATISFACTORY ○:FAIR(USUALLY OK FOR STATIC SEAL)

⊙: DOUBTFUL(SOMETIMES OF FOR STATIC SEAL) △:UNSATISFACTORY

×:INSUFFICIENT DATA

| Item \ Material | NBR | EPDM | FKM | CR | ACM | FVMQ | VMQ |
|---|---|---|---|---|---|---|---|
| BENZINE | ◎ | △ | ◎ | ○ | ◎ | ◎ | △ |
| BENZOIC ACID | △ | △ | ◎ | △ | △ | ○ | △ |
| BENZOPHENONE | × | ○ | ◎ | × | △ | ◎ | × |
| BENZYL ALCOHOL | △ | ○ | ◎ | ○ | △ | ○ | × |
| BLEACH LIQUOR | △ | ◎ | ◎ | △ | △ | ○ | ○ |
| BORAX | ○ | ◎ | ◎ | △ | ○ | ○ | ○ |
| BORIC ACID | ◎ | ◎ | ◎ | ◎ | △ | ◎ | ◎ |
| BRAKE FLUID (NON-PETROLEUM) | ⊙ | ◎ | △ | ○ | × | △ | ⊙ |
| BROMINE | △ | △ | ◎ | △ | △ | ○ | △ |
| BROMOBENZENE | △ | △ | ◎ | △ | △ | ◎ | △ |
| BUNKER OIL | ◎ | △ | ◎ | △ | ◎ | ◎ | ○ |
| BUTANE | ◎ | △ | ◎ | ◎ | ◎ | ◎ | △ |
| BUTTER-ANIMAL FAT | ◎ | ◎ | ◎ | ○ | ◎ | ◎ | ○ |
| N-BUTYL ACETATE | △ | ○ | △ | △ | △ | △ | △ |
| BUTYL ALCOHOL | ◎ | ○ | ◎ | ◎ | △ | ◎ | ○ |
| BUTYL AMINE OF N-BUTYL AMINE | ⊙ | △ | △ | △ | △ | △ | ○ |
| BUTYL CARBITOL | △ | ◎ | ⊙ | ⊙ | △ | △ | △ |
| BUTYL CELLOSOLVE | ⊙ | ○ | △ | ⊙ | △ | △ | × |
| BUTYRALDEHYDE | △ | ○ | △ | △ | △ | △ | △ |
| CARBITOL | ○ | ○ | ○ | ○ | △ | ○ | ○ |
| CARBITOL ACETATE | △ | △ | ◎ | △ | △ | × | △ |
| CARBON DISULFIDE | △ | △ | ◎ | △ | ⊙ | ◎ | × |
| CARBON TETRACHLORIDE | ○ | △ | ◎ | △ | △ | ○ | △ |
| CARBONIC ACID | ○ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ |
| CASTOR OIL | ◎ | ○ | ◎ | ◎ | ◎ | ◎ | ◎ |
| CELLOSOLVE | △ | ○ | △ | △ | △ | △ | △ |
| CHASSIS GREASE | ◎ | △ | ○ | ○ | ◎ | × | △ |
| CHLORACETIC ACID | △ | ○ | △ | △ | △ | △ | × |
| CHLORACETONE | △ | ◎ | ◎ | ○ | × | × | △ |
| CHLORODANE | ○ | △ | ◎ | ⊙ | × | ○ | △ |
| CHLORINE, DRY | △ | △ | ◎ | △ | △ | ◎ | △ |
| CHLORINE DIOXIDE | △ | ⊙ | ◎ | △ | △ | ○ | × |
| CHLORINE DIOXIDE, 8% CL AS $NAC10_2$ IN SOLUTION | △ | △ | ◎ | △ | △ | ○ | × |
| CHLORINE TRIFLUORIDE | △ | △ | △ | △ | △ | △ | △ |
| CHLORINE, WET | ⊙ | ○ | ◎ | △ | △ | ○ | × |

**COMPATIBILITY RATING**

◎:SATISFACTORY ○:FAIR(USUALLY OK FOR STATIC SEAL)

⊙: DOUBTFUL(SOMETIMES OF FOR STATIC SEAL) △:UNSATISFACTORY

×:INSUFFICIENT DATA

| Item \ Material | NBR | EPDM | FKM | CR | ACM | FVMQ | VMQ |
|---|---|---|---|---|---|---|---|
| CHLOROBENZOL | △ | △ | ◎ | △ | △ | × | △ |
| CHLOROFORM | △ | △ | ◎ | △ | △ | ○ | △ |
| CHLOROSULPHONIC ACID | △ | △ | △ | △ | △ | △ | △ |
| CHROME PLATING SOLUTIONS | △ | ○ | ◎ | △ | △ | ○ | ○ |
| CHROMIC ACID, 50% | △ | ○ | ◎ | △ | △ | ⊙ | ⊙ |
| CITRIC ACID | ◎ | ◎ | ◎ | ◎ | × | ◎ | ◎ |
| COD LIVER OIL | ◎ | ◎ | ◎ | ○ | ◎ | ◎ | ○ |
| COFFEE | ◎ | ◎ | ◎ | ◎ | △ | ◎ | ◎ |
| CORN OIL | ◎ | ⊙ | ◎ | ⊙ | ◎ | ◎ | ◎ |
| CREOSOTE, COAL TAR | ◎ | △ | ◎ | ○ | ◎ | ◎ | △ |
| CREOSOTE OIL | ◎ | △ | ◎ | ○ | × | × | ○ |
| CREOSYLIC ACID | △ | △ | ◎ | △ | △ | ○ | △ |
| CRUDE OIL | ○ | △ | ◎ | △ | ◎ | ○ | △ |
| CYCLOHEXANE | ◎ | △ | ◎ | ⊙ | ○ | ◎ | △ |
| CYCLOHEXNOL | ◎ | △ | ◎ | ○ | × | ◎ | △ |
| DECALIN | △ | △ | ◎ | △ | × | ◎ | △ |
| DENATURED ALCOHOL | ◎ | ◎ | ◎ | ◎ | △ | ◎ | ◎ |
| DIACETONE | △ | ◎ | △ | △ | △ | △ | △ |
| DIBUTYLAMINE | △ | △ | △ | ⊙ | △ | △ | ⊙ |
| DIBUTYL PHTHALATE | △ | ○ | ⊙ | △ | △ | ⊙ | × |
| DICHLORO ANILINE | △ | △ | ○ | △ | △ | × | △ |
| DICHLORO BUTANE | ○ | △ | ◎ | △ | △ | ○ | △ |
| DIESEL OIL | ◎ | △ | ◎ | ⊙ | ◎ | ◎ | △ |
| DIETHYLAMINE | ○ | ○ | △ | ○ | △ | △ | ○ |
| DIETHYL BENZENE | ○ | △ | ◎ | △ | × | × | × |
| DIETHYLENE GLYCOL | ◎ | ◎ | ◎ | ◎ | △ | ◎ | ○ |
| DIMETHYL ETHER | △ | △ | △ | ⊙ | ⊙ | ⊙ | △ |
| DIMETHYL FORMAMIDE | △ | ◎ | △ | × | × | × | ◎ |
| DIMETHYL PHTHALATE | △ | ◎ | ◎ | △ | △ | × | × |
| DIMETHYL TEREPHTHALATE | △ | △ | ◎ | △ | △ | × | △ |
| DIOCTYL PHTHALATE | △ | ○ | ○ | △ | △ | ○ | ⊙ |
| DIOXANE | △ | ○ | △ | △ | △ | △ | △ |
| DIPHENYL | △ | △ | ◎ | △ | △ | ○ | △ |
| DOW CORNING-550 | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ⊙ |
| DOW GUARD | ◎ | ◎ | ◎ | ◎ | ⊙ | ◎ | ◎ |
| DOWTHERM, A | △ | △ | ◎ | △ | △ | ○ | △ |

**COMPATIBILITY RATING**

◎:SATISFACTORY ○:FAIR(USUALLY OK FOR STATIC SEAL)

⊙: DOUBTFUL(SOMETIMES OF FOR STATIC SEAL) △:UNSATISFACTORY

×:INSUFFICIENT DATA

| Item \ Material | NBR | EPDM | FKM | CR | ACM | FVMQ | VMQ |
|---|---|---|---|---|---|---|---|
| DOWTHERM, E | △ | △ | ◎ | △ | △ | ○ | △ |
| ELCO 28-EP LUBRICANT | ◎ | △ | ◎ | ⊙ | ◎ | ◎ | ○ |
| EPOXY RESINS | × | ◎ | △ | ◎ | × | × | × |
| ETHANE | ◎ | △ | ◎ | ○ | ◎ | ○ | △ |
| ETHANOL | ◎ | ◎ | ⊙ | ◎ | △ | ◎ | ◎ |
| ETHANOL AMINE | ○ | ○ | △ | ○ | △ | △ | ○ |
| ETHYL ACETATE-ORGANIC ESTER | △ | ○ | △ | △ | △ | △ | ○ |
| ETHYL BENZENE | △ | ◎ | ◎ | △ | △ | ◎ | △ |
| ETHYL CELLULOSE | ○ | ○ | △ | ○ | △ | △ | ○ |
| ETHYL CHLORIDE | ◎ | ◎ | ◎ | ◎ | ⊙ | ◎ | △ |
| ETHYL ETHER | ⊙ | ⊙ | △ | △ | △ | ⊙ | △ |
| ETHYL FORMATE | △ | ○ | ◎ | ○ | × | ◎ | × |
| ETHYL HEXANOL | ◎ | ◎ | ◎ | ◎ | △ | ◎ | ○ |
| ETHYL MERCAPTAN | △ | ⊙ | △ | ○ | × | × | ⊙ |
| ETHYLENE CHLORIDE | △ | △ | ◎ | △ | △ | × | △ |
| ETHYLENE OXIDE | △ | ◎ | △ | △ | △ | × | △ |
| FORMALDEHYDE | ⊙ | ○ | △ | ⊙ | △ | △ | ○ |
| FORMIC ACID | ○ | ◎ | △ | ◎ | × | × | ○ |
| FREON 12 | ◎ | ○ | ◎ | ◎ | × | △ | △ |
| FUEL OIL | ◎ | △ | ◎ | ○ | ◎ | ◎ | △ |
| FURAN (FURFURAN) | △ | × | × | △ | △ | × | × |
| FURFURAL | △ | ○ | △ | △ | △ | × | △ |
| FURFURYL ALCOHOL | △ | ○ | × | △ | △ | △ | △ |
| FYRQUEL A60 | △ | ○ | △ | △ | △ | △ | ⊙ |
| GALLIC ACID | ○ | ○ | ◎ | ○ | △ | ◎ | × |
| GASOLINE | ◎ | △ | ◎ | △ | △ | ◎ | △ |
| GELATIN | ◎ | ◎ | ◎ | ◎ | △ | ◎ | ◎ |
| GLUCOSE | ◎ | ◎ | ◎ | ◎ | × | ◎ | ◎ |
| GLYCERINE-GLYCEROL | ◎ | ◎ | ◎ | ◎ | △ | ◎ | ◎ |
| N-HEPTANE | ◎ | △ | ◎ | ○ | ◎ | ◎ | △ |
| N-HEXALDEHYDE | △ | ◎ | △ | ◎ | × | △ | ○ |
| N-HEXANE | ◎ | △ | ◎ | ○ | ◎ | ◎ | △ |
| HEXANOL | ◎ | ○ | ◎ | ◎ | △ | × | ◎ |
| HOME HEATING OIL | ◎ | △ | ◎ | ○ | ◎ | × | ◎ |
| HYDRAZINE | ○ | ◎ | × | ○ | × | × | ○ |
| HYDROCYANIC ACID | ○ | ◎ | ◎ | ○ | △ | ○ | ⊙ |

**COMPATIBILITY RATING**

◎:SATISFACTORY ○:FAIR(USUALLY OK FOR STATIC SEAL)

⊙: DOUBTFUL(SOMETIMES OF FOR STATIC SEAL) △:UNSATISFACTORY

x:INSUFFICIENT DATA

| Item \ Material | NBR | EPDM | FKM | CR | ACM | FVMQ | VMQ |
|---|---|---|---|---|---|---|---|
| HYDROCHLORIC ACID, 3 MOLAR | ⊙ | ◎ | ◎ | ⊙ | ○ | ○ | △ |
| CONCENTRATED | △ | ⊙ | ◎ | △ | △ | ⊙ | △ |
| HYDROGEN PEROXIDE | ○ | ◎ | ◎ | ◎ | △ | ◎ | ◎ |
| 90% | △ | ⊙ | ◎ | △ | △ | ○ | ○ |
| HYDROGEN SULFIDE DRY, COLD | ◎ | ◎ | △ | ◎ | △ | ⊙ | ⊙ |
| DRY HOT | △ | ◎ | △ | ○ | △ | ⊙ | ⊙ |
| WET, COLD | △ | ◎ | △ | ◎ | △ | ⊙ | ⊙ |
| WET, HOT | △ | ◎ | △ | ○ | △ | ⊙ | ⊙ |
| HYDROQUINONE | ⊙ | △ | ○ | △ | △ | ○ | × |
| HYPOID GEAR LUBE | ◎ | △ | ◎ | ○ | ◎ | × | ○ |
| IODINE | ○ | ○ | ◎ | △ | × | ◎ | × |
| ISOCYANATE | × | × | ◎ | × | × | × | × |
| ISO OCTANE | ◎ | △ | ◎ | ○ | ◎ | ◎ | △ |
| ISOPHORONE (KETONE) | △ | ◎ | △ | △ | △ | △ | △ |
| ISOPAR | ◎ | △ | ◎ | ◎ | ◎ | × | △ |
| ISOPROPANOL | ○ | ◎ | ◎ | ○ | △ | ○ | ◎ |
| ISOPROPYL ACETATE | △ | ○ | △ | △ | △ | △ | △ |
| JP-4 (MIL-J-5624) | ◎ | △ | ◎ | △ | ○ | ○ | △ |
| JP-5 (MIL-J-5624) | ◎ | △ | ◎ | △ | ○ | ○ | △ |
| KEROSINE | ◎ | △ | ◎ | ○ | ◎ | ◎ | △ |
| LACTIC ACID, COLD | ◎ | ◎ | ◎ | ◎ | △ | ◎ | × |
| HOT | △ | △ | ◎ | △ | △ | ○ | × |
| LACQUERS | △ | △ | △ | △ | △ | △ | △ |
| LARD, ANIMAL FAT | ◎ | ○ | ◎ | ○ | ◎ | ◎ | ○ |
| LINOLEIC ACID | ○ | △ | ○ | ○ | × | × | ○ |
| LINSEED OIL | ◎ | ⊙ | ◎ | ⊙ | ◎ | ◎ | ◎ |
| LYE SOLUTIONS | ○ | ◎ | ○ | ○ | △ | ○ | ○ |
| MALATHION | ○ | △ | ◎ | × | × | ○ | △ |
| MALEIC ACID | △ | △ | ◎ | △ | △ | × | × |
| MERCURY | ◎ | ◎ | ◎ | ◎ | × | × | × |
| METER-CRESOL | △ | △ | ◎ | ◎ | △ | × | △ |
| METHANE | ◎ | △ | ◎ | ○ | ◎ | ○ | △ |
| METHANOL | ◎ | ◎ | △ | ◎ | △ | ◎ | ◎ |
| METHYL ACETATE | △ | ○ | △ | ○ | △ | △ | △ |
| METHYLACRYLIC ACID | △ | ○ | ⊙ | ○ | △ | △ | △ |

**COMPATIBILITY RATING**

◎:SATISFACTORY ○:FAIR(USUALLY OK FOR STATIC SEAL)

⊙: DOUBTFUL(SOMETIMES OF FOR STATIC SEAL) △:UNSATISFACTORY

×:INSUFFICIENT DATA

| Item \ Material | NBR | EPDM | FKM | CR | ACM | FVMQ | VMQ |
|---|---|---|---|---|---|---|---|
| METHYL CELLOSOLVE | ⊙ | ○ | △ | ⊙ | △ | △ | △ |
| METHYL CHLORIDE | △ | ⊙ | ◎ | △ | △ | ○ | △ |
| METHYL ETHYL KETONE (MEK) | △ | ◎ | △ | △ | △ | △ | △ |
| METHYL MERCAPTAN | × | ◎ | × | × | × | × | × |
| MINERAL OILS | ◎ | ⊙ | ◎ | ○ | ◎ | ◎ | ○ |
| MINERAL SPIRITS | ◎ | △ | ◎ | △ | ◎ | × | △ |
| MONOVINYL ACETYLENE | ◎ | ◎ | ◎ | ○ | × | × | ○ |
| MUSTARD | × | ◎ | ◎ | × | × | × | ◎ |
| NAPHTHA | ○ | △ | ◎ | △ | ○ | ○ | △ |
| NAPHTHALENE | △ | △ | ◎ | △ | × | ◎ | △ |
| NAPHTHENIC ACID | ○ | △ | ◎ | △ | × | ◎ | △ |
| NATURAL GAS | ◎ | △ | ◎ | ◎ | ○ | ⊙ | ◎ |
| NEATSFOOT OIL | ◎ | ○ | ◎ | △ | ◎ | ◎ | ○ |
| NITRIC ACID | | | | | | | |
| 3 MOLAR | △ | ○ | ◎ | △ | △ | ⊙ | △ |
| CONCENTRATED | △ | △ | ◎ | △ | △ | ⊙ | △ |
| RED FUMING (RFNA) | △ | △ | ○ | △ | △ | △ | △ |
| INHIBITED RED FUMING (IRENA) | △ | △ | ○ | △ | △ | △ | △ |
| NITROBENZENE | △ | △ | ○ | △ | △ | △ | △ |
| NITROPROPANE | △ | ○ | △ | △ | △ | △ | △ |
| N-OCTANE | ○ | △ | ◎ | △ | △ | ○ | △ |
| OCTANOL | ◎ | ◎ | ◎ | ◎ | △ | × | ◎ |
| OLEIC ACID | ⊙ | △ | ○ | △ | △ | × | △ |
| OLEUM (FUMING SULFURIC ACID) | △ | △ | ◎ | △ | △ | × | △ |
| ORONITE 8200 | ○ | △ | ◎ | ◎ | × | ◎ | △ |
| OXALIC ACID | ○ | ◎ | ◎ | ○ | × | ◎ | ○ |
| PEANUT OIL | ◎ | ⊙ | ◎ | ⊙ | ◎ | ◎ | ◎ |
| PENTANE, 2 METHYL | ◎ | △ | ◎ | ○ | ◎ | ⊙ | △ |
| 2-4, DIMETHYL | ◎ | △ | ◎ | ○ | ◎ | ⊙ | △ |
| 3-METHYL | ◎ | △ | ◎ | ○ | ◎ | ⊙ | △ |
| PERCHLOROETHYLENE | ○ | △ | ◎ | △ | △ | ○ | △ |
| PETROLEUM ETHER | △ | △ | ◎ | △ | △ | × | △ |
| PHENOL | △ | △ | ◎ | △ | △ | ○ | △ |
| PHENYLHYDRAZINE | △ | △ | ◎ | △ | △ | × | × |
| PINE OIL | ◎ | △ | ◎ | △ | × | ◎ | △ |
| POTASSIUM HYDROXIDE, 50% | ○ | ◎ | △ | ○ | △ | ⊙ | ⊙ |

**COMPATIBILITY RATING**

◎:SATISFACTORY ○:FAIR(USUALLY OK FOR STATIC SEAL)

⊙: DOUBTFUL(SOMETIMES OF FOR STATIC SEAL) △:UNSATISFACTORY

×:INSUFFICIENT DATA

| Material / Item | NBR | EPDM | FKM | CR | ACM | FVMQ | VMQ |
|---|---|---|---|---|---|---|---|
| PHOSPHORIC ACID | | | | | | | |
| 3 MOLAR | △ | ◎ | ◎ | ⊙ | × | ○ | ○ |
| CONCENTRATED | △ | ○ | ◎ | △ | × | ○ | ⊙ |
| PROPANE | ◎ | △ | ◎ | ○ | ◎ | ○ | △ |
| PROPANOL | ◎ | ◎ | ◎ | ◎ | △ | × | ◎ |
| PROPYL ACETATE | △ | ○ | △ | △ | △ | △ | △ |
| PYDRAUL 10E, 29ELT | △ | ◎ | ◎ | △ | △ | △ | △ |
| 30E, 50E, 65E, 90E | △ | ◎ | ◎ | △ | △ | ◎ | ◎ |
| 115E | △ | ◎ | ◎ | △ | △ | ⊙ | △ |
| 230E, 312C, 540C | △ | △ | ◎ | △ | △ | △ | △ |
| PYRANOL | ◎ | △ | ◎ | ◎ | ◎ | × | △ |
| PYRIDINE | △ | △ | △ | △ | △ | × | △ |
| RAPESEED OIL | ○ | ◎ | ◎ | ○ | ○ | ◎ | △ |
| SAE10W30 | ◎ | △ | ◎ | ○ | ◎ | × | ◎ |
| SEA (SALT) WATER | ◎ | ◎ | × | ○ | △ | ◎ | ◎ |
| SILICONE GREASES | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ | ⊙ |
| SILVER NITRATE | ○ | ◎ | ◎ | ◎ | ◎ | ◎ | ◎ |
| SKELLY, SOLVENT B, C, E | ◎ | △ | ◎ | △ | × | ◎ | × |
| SKYDROL | △ | ◎ | ◎ | △ | △ | × | △ |
| SKYDROL 500 | △ | ◎ | △ | △ | △ | ⊙ | ⊙ |
| SODIUM HYDROXIDE, 3 MOLAR | ○ | ◎ | ○ | ○ | △ | ○ | ◎ |
| SOVASOL NO. 1,2 AND 3 | ◎ | △ | ◎ | ○ | ○ | ◎ | △ |
| NO. 73 AND 74 | ○ | △ | ◎ | ○ | ○ | ◎ | △ |
| SOYBEAN OIL | ◎ | ⊙ | ◎ | ⊙ | ◎ | ◎ | ◎ |
| STEARIC ACID | ○ | ○ | × | ○ | × | × | ○ |
| STODDARD SOLVENT | ◎ | △ | ◎ | ○ | ◎ | ◎ | △ |
| SUCROSE SOLUTIONS | ◎ | ◎ | ◎ | ○ | △ | ◎ | ◎ |
| SULFURIC ACID | | | | | | | |
| 3 MOLAR | △ | ○ | ◎ | ⊙ | ○ | ⊙ | △ |
| CONCENTRATED | △ | △ | ◎ | △ | △ | △ | △ |
| TALL OIL | ◎ | △ | ◎ | ○ | ◎ | × | × |
| TANNIC ACID | ◎ | ◎ | ◎ | ○ | △ | × | ○ |
| 10% | ◎ | ◎ | ◎ | ◎ | △ | ◎ | ○ |
| TAR, BITUMINOUS | ○ | △ | ◎ | ⊙ | △ | ◎ | ○ |
| TARTARIC ACID | ◎ | ○ | ◎ | ○ | × | ◎ | ◎ |
| TETRACHOROETHANE | △ | △ | ◎ | △ | △ | ○ | × |

**COMPATIBILITY RATING**

◎:SATISFACTORY ○:FAIR(USUALLY OK FOR STATIC SEAL)

⊙: DOUBTFUL(SOMETIMES OF FOR STATIC SEAL) △:UNSATISFACTORY

x:INSUFFICIENT DATA

| Item \ Material | NBR | EPDM | FKM | CR | ACM | FVMQ | VMQ |
|---|---|---|---|---|---|---|---|
| TETRALIN | △ | △ | ◎ | △ | × | ◎ | △ |
| TIDEWATER OIL-BEEDOL | ◎ | △ | ◎ | ○ | ◎ | ◎ | ○ |
| MULTIGEAR 140, EP LUBE | ◎ | △ | ◎ | ○ | ◎ | ◎ | △ |
| TOLUENE | △ | △ | ◎ | △ | △ | ○ | △ |
| TRICHLOROETHYLENE | ⊙ | △ | ◎ | △ | △ | ○ | △ |
| TRIETHANOL AMINE | ⊙ | ○ | △ | ○ | △ | △ | × |
| TURBINE OIL | ◎ | △ | ◎ | △ | ◎ | ◎ | △ |
| TURPENTINE | ◎ | △ | ◎ | △ | ○ | ○ | △ |
| UCDN 50HB 280X | ◎ | ◎ | ◎ | ◎ | × | × | ◎ |
| UNIVIS J-43 | ◎ | △ | ◎ | ◎ | ◎ | × | △ |
| VARNISH | ○ | △ | ◎ | △ | △ | ○ | △ |
| VINEGAR | ○ | ◎ | ◎ | ○ | △ | ⊙ | ◎ |
| WATER | ◎ | ◎ | ○ | ○ | △ | ◎ | ◎ |
| WHEAT GERM OIL | ◎ | △ | ◎ | ○ | ◎ | × | ◎ |
| WHISKEY AND WINES | ◎ | ◎ | ◎ | ◎ | △ | ◎ | ◎ |
| WOOD OIL | ◎ | △ | ◎ | ○ | × | ○ | △ |

**COMPATIBILITY RATING**

◎:SATISFACTORY ○:FAIR(USUALLY OK FOR STATIC SEAL)

⊙: DOUBTFUL(SOMETIMES OF FOR STATIC SEAL) △:UNSATISFACTORY

x:INSUFFICIENT DATA